

nanorods were synthesized according to the conventional seed-mediated growth protocol and characterized by UV-Vis spectroscopy, transmission electron microscopy (TEM), and atomic absorption spectroscopy (AAS) for shape, size and yield determination. The typical surface plasmon absorption bands in the visible and near IR region confirmed the rod morphology of the nanostructures. Phosphate, Tris and HEPES buffer solutions were prepared and the pH was adjusted to be 7.4. Concentration of the buffer solutions was 0.05 M in the final working solutions. Prior to use, GNRs were purified by two rounds of centrifugation at 12000 rpm, for 6 minutes. Pellet of the second round with a fixed concentration of gold nanorods were diluted with each buffer solution. UV-Vis spectra of the interacted samples were recorded to monitor the plasmonic bands. Results showed that neither the transverse SPR nor the longitudinal one have changed notably. Although the intensity of LSPR peak has been somewhat affected in buffer medium, the rod morphology is still maintained. Sensitivity of gold nanorods to trace changes in the local environment/ refractive index encourages the possibility of utilizing these nanostructures in development of nanostructures for various biosensing applications.

Keywords: Gold Nanorods, Surface Plasmon Resonance, Nanobiosensor.

Abstract No.249

Investigation of Mechanistic Influence of Mutation D117G in Aequorin from *Aequorea Victoria*: a Molecular Dynamics Simulation Study

Somayeh Asfaei, Ammar Mohseni, Majid Taghdir*

Department of Biology, Faculty of Science, University of Guilan, Rasht, IR
(E-mail: Asfaeisomayeh@yahoo.com)

The photoprotein aequorin, isolated from the jellyfish *Aequorea victoria*, is a bioluminescent complex formed with the protein apoaequorin and the prosthetic factor coelenterazine that emits light upon calcium binding. In order to understand the mechanism of the reaction, the study of structure-function relationships was undertaken with respect to modifying certain of its amino acid residues. One of these mutations is the D117G that is located out of substrate binding cavity and Ca²⁺-binding loops. In this study short time molecular dynamics simulations were performed to investigate the influence of this fine change on dynamic properties of substrate binding cavity and Ca²⁺ binding loops that direct emission light properties in this photoprotein. Previous studies showed that this mutation decreases affinity of loops to Ca²⁺ and increase half-life of emission light in the

photoprotein. Our finding revealed that the replacement of ASP with GLY alters dynamics and energetic properties in functional regions of the structure and affects emission light and Ca²⁺-sensitivity properties in photoprotein.

Keywords: Aequorin, Molecular Dynamic Simulation, Ca²⁺-affinity, Life-time.

Abstract No.250

Surface Modification of Gold Nanorods with Polyethyleneglycol for Nano Biosensing Applications

*Tahereh Tohidi Moghadam, Bijan Ranjbar**

Department of Nanobiotechnology Faculty of Biological Sciences
Tarbiat Modares University, IR
(E-mail: t.tohidi@modares.ac.ir)

There has been great interest in the domain of nanobiotechnology to design and develop new generation of nanobiosensors. Amongst anisotropic nanoparticles, gold nanostructures of rod morphology (GNRs) have attracted significant attention, for having variety of applications in biomedicine and biosensing. Although many fruitful features of gold nanorods have been introduced so far, the nanostructure itself is believed to show strong cytotoxicity, since it has been synthesized in the presence of hexadecyltrimethylammonium bromide (CTAB). The cationic surfactant is also known to play important role in the stabilization of GNRs, and maintenance of rod morphology. Herein, polyethyleneglycol has been utilized for neutralization of the positively charged GNRs. Gold nanorods were synthesized according to the conventional seed mediated protocol. Formation of the rod morphology, size, monodispersity, concentration and yield of synthesis were characterized by UV-Vis spectroscopy, transmission electron microscopy (TEM) and atomic absorbance spectroscopy (AAS). Excess CTAB was removed by one round of centrifugation at 12000 rpm for 6 minutes. Sample of GNRs with 75 nM concentration was interacted with 400 μ L PEG-4000 (600 mg. mL⁻¹). The mixture was incubated at ambient temperature for 1 hour. Excess PEG was removed by another round of centrifugation. Surface plasmon resonance of bare and pegylated GNRs was monitored via UV-Vis spectrophotometer. Results showed that transverse plasmon resonance (TSPR) and longitudinal plasmon resonance (LSPR) appeared at 528 nm and 708 nm, respectively. Intensity of SPR bands of the pegylated GNRs decreased upon treatment, without any shift in both regions. Although a considerable quantity of the cationic surfactant has been replaced by polyethyleneglycol, stability of GNRs

and their typical SPR absorption bands has not undergone undesirable change. Pegylated gold nanorods could be utilized for in-vivo applications, such as drug delivery with higher circulation time, photothermal therapy, and nanobiosensors of more specificity in the upcoming research fields of nanobiotechnology.

Keywords: Nanobiosensor, Gold Nanorods, Surface plasmon Resonance.

Abstract No.251

Lipase Applying in Soybean Oil to Biodiesel Production and Comparison with Chemical Method

*Ahmad Panahazar*¹, Shiva Irani¹, Saleh Soleimani¹,
Seyed Mohammad Atyabi², Dariush Norouzi²*

1. Department of Biology, Science and Research Branch, Islamic Azad University, Tehran, IR
2. Pilot Biotechnology Department, Pasteur Institute of Iran, Tehran, IR (E-mail: Apanahazari@yahoo.com)

Nowadays, biodiesel is well accepted as a renewable energy. Biodiesel is a fuel comprised of monoalkyl esters traditionally derived from vegetable oils or animal fats. There is currently an unprecedented increased interest, demand for biodiesel and other fuels derived from renewable biomass. Our study was conducted to investigate the optimum conditions for biodiesel formation from soybean oil with chemical reaction and lipase enzyme. The results indicated that increasing of temperature is important factor in both methods. In this study through experimental investigation of reaction conditions such as, reaction temperature which are deemed to have main impact on reaction conversion efficiency. The oil conversion was influenced by the methanol/oil molar ratio. The technical tools and processes for monitoring the transesterification reactions like GC have also been summarized. The experimental results showed that in chemical method a 1:8 molar ratio of methanol and ethanol to oil, addition of 1% wt KOH catalyst, 60 °C reaction temperature gave the best results, and the biodiesel yield exceeded 95% at 90 min. In enzymatic a 1:4 molar ratio of methanol to oil, 45 °C reaction temperature are best condition in biodiesel production. Enzyme stability and activity was investigated in present of methanol and tert-butanol. Methanol play a reducing role in affecting enzyme stability but tert-butanol increased the enzyme activity.

Keywords: Biodiesel, Triglyceride, Gas Chromatography, Transesterification, Base Methods.

Abstract No.252

Effect of DMSO & Triton on G-quadruplex-Hemin Interaction

*Zahra Karami¹, Bijan Ranjbar*¹,
Arastoo Badoei-Dalfard²*

1. Faculty of Biological Sciences, Department of Biophysics, Tarbiat Modares University, Tehran, IR
2. Faculty of Science, Department of Biology, Shahid Bahonar University of Kerman, Kerman, IR
(E-mail: z.karami@modares.ac.ir)

It has been reported that complexes formed by hemin and some G-quadruplexes can be developed as a new class of DNAzyme with peroxidase activity. DNA in single-stranded form has the ability to fold into complex structures that serve as highly specific catalysts. Here, we report metal ions induced guanine quadruplex formation with d(GTG3TAG3CG3T2G2), which shows peroxidase function upon complexation with hemin. DNA oligomers were heated at 88°C in distilled water and gradually cooled. The DNAs were then treated in HEPES buffer in the presence and absence of DMSO and Triton and both of them were kept at room temperature to allow proper folding. An equivalent volume of hemin was added to the G-quadruplex solution, and incubated to form DNAzyme complex. Spectroscopic measurements were carried out in order to characterize complex formation. The UV-vis spectroscopy results showed that the uncomplexed hemin has a Soret absorption band centered at 397 nm. Upon incubation with G-DNA, in the presence of DMSO and Triton, the absorption center showed a slight red shift to 404 nm with hyperchromicity. This characteristic has been used to investigate the hemin-DNA interaction. However, in the absence of Triton and DMSO, only hyperchromicity and considerable blue shift was observed. By using Triton and DMSO alone, the significant results were obtained. There was no change in the intensity of Hemin-G-quadruplex interaction when using DMSO and hyperchromicity was not observed. But after using Triton in the buffer composition hyperchromicity and red shift was observed in comparison with DMSO.

Keywords: Hemin, Deoxyribozyme, Peroxidase, DMSO, DNAzyme.
